



we know how
since 1962

WATERPROOFING MEMBRANES

ELASTOMERIC BITUMINOUS MEMBRANES (SBS)

ESHAELASTAN-S

Elastomeric Bituminous Waterproofing Membranes
(SBS -20°C)



GENERAL DESCRIPTION

Elastomeric waterproofing membranes **EshaElastan-S** are produced from special bitumen, modified with thermoplastic elastomeric materials (SBS). This modification results in a binding material with enhanced elasticity, even at extremely low temperatures (-20 °C), and improved viscoelastic properties which are ideal for the production of superb quality bituminous waterproofing products.

The selection of the appropriate combination of reinforcement, surface finishing and weight/thickness of the membrane offers a variety of applications and high quality solutions in every problem of waterproofing, like:

- Waterproofing of flat and inclined roofs
- Waterproofing of metal decks
- Re-roofing, refurbishment
- Waterproofing of underground works / Foundations
- Waterproofing of bridge-decks & parking decks
- Waterproofing of reservoirs (tanks) and canals

REINFORCEMENT

EshaElastan-S possible reinforcements are:

- Spunbond Polyester (SP) of great durability, which gives the membrane increased resistance to mechanical deformations (cracking, puncture, tearing etc.) and an extended stretching ability.
- High stability composite polyester fabric with embedded glass yarns in order to maximize torching membrane's stability & eliminate "banana" effects.
- High quality glass fleece which gives the membrane dimensional stability.

CHARACTERISTICS/ADVANTAGES

As a result of their high quality **EshaElastan-S** membranes offer the following advantages:

- ▶ Great elasticity (ability to stretch and recoil to it's initial dimensions). Elastic recovery value for the membrane's modified compound exceeds 90%.
- ▶ High flexibility at low temperatures (-20°C) compared with other types of bituminous membranes.
- ▶ Consistent waterproofing properties on a long term basis.
- ▶ Wide temperature application window & operating range.
- ▶ High resistance to cracking, owing to its elastic properties.
- ▶ High puncture resistance and resistance to mechanical deformations.
- ▶ Advanced weldability to any substrate.
- ▶ Increased resistance to ageing.

Alfa-Alfa Energy S.A.

ATHENS | CENTRAL OFFICES-FACORY: Aspropyrgos Beach, 193 00 Aspropyrgos, Attica | T. +30 210 5518 700
THESSALONIKI | OFFICES-WAREHOUSE: 18 Epirou Street, 570 09 Kalochori | T. +30 2310 783 725
www.asha.gr • sales@asha.gr



ESHAELASTAN-S

Elastomeric Bituminous
Waterproofing Membranes
(SBS -20°C)

SURFACE FINISH

EshaElastan-S possible finishes include:

- Mineral chipping in various colors (green-gray, white, red-brown), when exposed to sunlight.
- A thin film of polyethylene for cases where the waterproofing layer is protected by other materials (tiles, concrete, etc.).
- High reflective aluminium foil.
- Paintable woven polypropylene fabric.

STORAGE

Membrane rolls should be stored in their original package, in vertical position, protected from direct sunlight, rain, snow and ice. In cold weather it is recommended that the rolls should be kept at temperature >5°C for at least 10 hours before installation.

Avoid strong and sudden roll impact, as well as fast unrolling during installation, transportation and storage, at low temperature conditions.

APPLICATION PROCEDURE

Surface preparation

- Before application of the membrane it is necessary to prepare properly the substrate surface. The substrate surface must be thoroughly cleaned, remove all dust, loose matter and remaining oils in order to be smooth and dry.
- Recommended surface slope: 1.5% minimum.
- Recommended substrate relative moisture $\leq 6\%$.
- The surface must be primed with eco friendly (VOCs free), elastomeric, waterproofing, bituminous primer with new generation technology **EshaTopprimer** at a consumption $\sim 0.3 \text{ Lt/m}^2$.
- Alternatively the surface can be primed with **EshaLac 50-S** at a consumption $\sim 0.3 \text{ Lt/m}^2$.
- As soon as the surface is tack-free, the bituminous membrane can be torch applied.

Application of the bituminous membrane

- To avoid water vapor condensation and localized stresses that can lead to local surface cracking, it is recommended to apply a separating/ventilating layer by installing a special **EshaPerfo** or **EshaVent** or by another similar method of separating the waterproofing membrane **EshaElastan-S**.
- Membrane application starts from the lowest point of slopes in order to secure unobstructed water flow, when membranes are torched one in parallel to the other.
- The membrane is then rolled and positioned parallel to its adjacent one. It is then rerolled half-way without shifting.
- The bottom surface of the re-rolled part is heated with a propane torch until bitumen becomes fluid and the membrane is unrolled again to apply evenly on the substrate.

CERTIFICATION

Esha Bituminous membranes comply with **EN 13707**, **EN 13969** and are certified with **CE No.1020-CPR-010021423**.

Application to roofs according to **EN 13707** and underground structures according to **EN 13969**.

For all available certificates and certifications please contact Esha Sales Department.



EPD certification is an independent assessment of a product's environmental impact throughout its entire life cycle, from initial production to disposal or recycling at the end of its life cycle. It contributes points to some of the leading green building programs, such as LEED certified building projects.



we know how
since 1962

ESHAELASTAN-S

- Longitudinal overlaps must be at least 8 cm while transversal ones must be kept to a minimum of 15 cm.
- Overlapping joints are treated with a metallic lapjoint cylinder in order to apply the optimal pressure in these demanding areas.
- In multiple layer waterproofing, application of the successive layers follows the same procedure and is done in the same direction as the previous ones. Care is taken so that overlaps do not coincide with those of the previous layer.
- In a ballasted roofing, a well calculated ballast should be placed on an adequate membrane protection layer to avoid damage.

Application notes

- Application temperature should be higher than 5°C.
- Waterproofing should be carried out by technicians, properly trained and certified in the bituminous membranes application.

For a more detailed description of bituminous waterproofing membranes' application please contact Esha Sales Department




WATERPROOFING MEMBRANES

ELASTOMERIC BITUMINOUS
MEMBRANES (SBS)

Elastomeric Bituminous Waterproofing Membranes (SBS -20°C)

Today, Esha is the No. 1 producer of bituminous waterproofing membranes in Greece, while also offering more than 500 specialized products (emulsions and solutions for surface protection and waterproofing, joint sealing materials, acrylics, epoxies, polyurethanes, polysulfides, modified road asphalt (elastomers, plastomers, recycled tires), asphalt road emulsions, asphalt bridge waterproofing materials, polyurethane thermal insulation boards, etc.).



See the products
and their applications
on our new website
www.esha.gr



we know how
since 1962

WATERPROOFING MEMBRANES

ELASTOMERIC BITUMINOUS
MEMBRANES (SBS)

ESHAELASTAN-S

Elastomeric Bituminous
Waterproofing Membranes
(SBS -20°C)

ΤΕΧΝΙΚΑ ΧΑΡΑΚΤΗΡΙΣΤΙΚΑ

Characteristics	Standards	T	Nominal values					Units
			Glass Fleece	Non woven polyester	Polyester combined with reinforcing glass yarns	Spun Bond polyester (SP-180)	Spun Bond polyester (SP-250)	
Length	EN 1849-1	±0.02	8 or 10	8 or 10	8 or 10	8 or 10	8 or 10	m
Width	EN 1849-1	-	1	1	1	1	1	m
Upper surface covering	-	-	PE film/mineral granules/aluminium foil					---
Bottom surface covering	-	-	PE film/Quartz sand					---
Thickness	EN 1849-1	±0.2	2.5 - 5	2.5 - 5	2.5 - 5	2.5 - 5	2.5 - 5	mm
Weight	EN 1849-1	±10%	3-6	3-6	3-6	3-6	3-6	kg/m ²
Type of bituminous mixture	-	-	Elastomeric (SBS)					---
Softening Point	EN 1427	≥	120	120	120	120	120	°C
Penetration at 25°C	EN 1426	± 5	30	30	30	30	30	dmm
Elastic recovery of the bituminous binder of the membrane	EN 13398	≥	90	90	90	90	90	%
Elastic recovery after the oxidative aging, EN 12607-1	EN 13398	≥	80	80	80	80	80	%
Tensile strength L/T	EN 12311-1	± 20%	320/220	400/300	540/500	900/650	1050/850	N/50mm
Elongation L/T	EN 12311-1	± 15%	2/2	30/45	45/55	50/60	50/60	%
Tear resistance L/T	ASTM D4073-94	± 15%	100/250	200/320	230/380	360/550	600/700	N
Static puncture resistance (concrete)	EN 12730/ UEAtc MOAT27	-	L2 (7-15)	L3 (15-25)	L3 (15-25)	L3 (15-25)	L4 (>25)	kg
Dynamic puncture resistance (concrete)	EN 12691/ UEAtc MOAT27	-	I3(Φ10)	I3(Φ8)	I3(Φ8)	I3(Φ8)	I3(Φ8)	mm
Flexibility to low temperatures	EN 1109	± 5	-20	-20	-20	-20	-20	°C
Water tightness (72 h)	UEAtc/EN 1928	≥	Successfully Passed (≥2)					bar
Vapor permeability coefficient	EN 1931	≥	20000	20000	20000	20000	20000	---
Heat resistance	EN 1110	≤	110	110	110	110	110	°C
Reaction to fire	EN 13501-1	-	F	F	F	F	F	---
Dimensional stability L/T	EN 1107-1	≤	-0.1/+0.1	-0.15/+0.1	-0.15/+0.1	-0.4/+0.3	-0.4/+0.3	%
Thermal conductivity	-	-	0.2	0.2	0.2	0.2	0.2	W/mK

Fluctuations in nominal values are in accordance with the relevant standards. The manufacturer reserves the right to modify the properties of its products. Esha provides information and, in particular, recommendations regarding the application and end use of its products based on its current knowledge and experience, when the products are stored, used, and applied under normal conditions. In practice, there are variations in substrates and local application conditions, so Esha cannot guarantee the success of the application of any material. It is recommended that the user test the application of the material under the local application conditions.